



alpha
wax

Carisma 55 T

Product data

| Property | Method | Unit | Specifications |
|------------------------------------|------------|--------------------|------------------|
| Congealing Point | ASTM D938 | °C | 54 – 56 |
| Color, Saybolt | ASTM D156 | - | min. + 28 |
| Needle Penetration at 25 °C | ASTM D1321 | dmm | 18 – 25 |
| Oil Content | ASTM D721 | % (m/m) | max 1,0 |
| Kinematic Viscosity at 100 °C | ASTM D445 | mm ² /s | 3,0 – 4,0 |
| Density at 70 °C | ASTM D4052 | kg/m ³ | 770 – 800 |
| Purity Requirement Candle Industry | RAL-GZ041 | - | Complies |
| Purity Requirement Eur. Pharm. | Eur.Pharm. | - | Complies |
| Purity Requirement FDA | § 172.886 | - | Complies |

Revision date: 26-06-2017

We reserve the right to change the specifications as a result of technical progress or for reasons related to production. Information contained in this technical literature is believed to be accurate and is offered in good faith to the customer. Alpha Wax however, cannot assume any liability or risk involved in the use of its products since the condition of use is beyond our control.