

CHU 610-Polyethylene Wax

Product data

| Property | Method | Unit | Specifications |
|----------------------|----------------|------|---------------------------|
| Softening Point | ASTM D6090-99 | °C | 113-121 |
| Color | QST-078 | | White to off-white |
| Penetration at 25 °C | ASTM D1321-02a | dmm | max. 9 |
| Viscosity at 149 °C | ASTM D1986-91 | cP | 55-300 |
| Flash point | ASTM D93-02a | °C | min. 193 |

CHU 610 meets the following requirements for Indirect Food Contact under FDA Regulations 21 CFR Parts 175.105, 175.125, 175.300, 175.320, 176.170, 176.180, 177.1210 and 177.2600.

Revision date: 05-07-2017

We expressly disclaim any warranties of merchant ability or fitness expressed or implied, as to the suitability of CHU 610 for use in any secondary products including the actual results of its use in any such product. We also expressly disclaim the above warranties resulting from the use of this products or any sample of this product in any secondary products.