



## CWP 500E Polyethylene Wax

---

### Product data

Property	Method	Unit	Specifications
Softening Point	ASTM D6090-99	°C	<b>107-116</b>
Color Klett	QST078		<b>max. 200</b>
Penetration at 25 °C	ASTM D1321-02a	dmm	<b>max. 8</b>
Viscosity at 149 °C	ASTM D1986-91	cP	<b>max. 50</b>
Flash point	ASTM D93-02a	°C	<b>min. 205</b>

CWP 500E meets the following requirements for Indirect Food Contact under FDA Regulations 21 CFR Parts 175.105, 175.125, 175.300, 175.320, 176.170, 176.180, 177.1210 and 177.2600.

---

Revision date: 05-07-2017

We expressly disclaim any warranties of merchant ability or fitness expressed or implied, as to the suitability of CWP 500E for use in any secondary products including the actual results of its use in any such product. We also expressly disclaim the above warranties resulting from the use of this products or any sample of this product in any secondary products.