



alpha  
wax

# Carisma Glossy

---

## Tentative Product data

| Property                       | Method     | Unit               | Specifications   |
|--------------------------------|------------|--------------------|------------------|
| Congealing Point               | ASTM D938  | °C                 | <b>57 - 60</b>   |
| Color, Saybolt                 | ASTM D156  | -                  | <b>min +25</b>   |
| Needle Penetration at 25 °C    | ASTM 1321  | dmm                | <b>11 - 15</b>   |
| Kinematic Viscosity at 100 °C  | ASTM D445  | mm <sup>2</sup> /s | <b>4,2 - 4,8</b> |
| Density at 70 °C               | DIN 51 757 | kg/m <sup>3</sup>  | <b>770</b>       |
| Requirement Candle Industry    | RAL-GZ041  | -                  | <b>Complies</b>  |
| Purity Requirement Eur. Pharm. | Eur.Pharm. | -                  | <b>Complies</b>  |
| Purity Requirement FDA         | § 172.886  | -                  | <b>Complies</b>  |

---

Revision date: 17-09-2019

We reserve the right to change the specifications as a result of technical progress or for reasons related to production. Information contained in this technical literature is believed to be accurate and is offered in good faith to the customer. Alpha Wax however, cannot assume any liability or risk involved in the use of its products since the condition of use is beyond our control.